

Alathon®

# L 5005

High Density Polyethylene

HMW Film Grade

Melt Index 0.057 Density 0.949

## Applications

ALATHON L 5005 is a high molecular weight high density copolymer that provides broad bimodal molecular weight distribution, high stiffness and good heat seal response and strength. Typical applications include merchandise bags, grocery sacks, trash can liners, produce bags and roll stock.

## Certification

L 5005 meets the requirements of the Food and Drug Administration regulation 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "...articles or components of articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information.

## Processing Techniques

Specific recommendations for processing L 5005 can only be made when the processing conditions, equipment and end use are known. For further suggestions, please contact your Equistar sales representative.

## Physical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index	0.057	g/10 min	D 1238
Density	0.949	g/cc	D 1505
Total Energy Dart Drop	2.05	ft-lbs/mil	D 3420
Elmendorf Tear Strength, MD (TD)	14 (35)	g	D 1922
Tensile Strength @ Yield, MD (TD)	3,800 (3,400)	psi	D 882
Tensile Strength @ Break, MD (TD)	8,500 (5,000)	psi	D 822
Elongation @ Break, MD (TD)	300 (420)	%	D 882
Secant Modulus, MD (TD)	115,000 (140,000)	psi	D 882

## Typical Process Condition Ranges:

BUR=3.5-4.5:1; Neck Height=6-9 Die Diameters; Die Gap (nominal), in.=0.040-0.050; Tower Height=Relatively Short; Output, Lb/Hr/In of Die Circumference=10-12; Melt Temperature - 390-420°F (199-216°C)

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at (800) 700-0946

®Alathon is a trademark of Equistar Chemicals, LP.

Equistar Chemicals, LP  
1221 McKinney, Suite 700  
P.O. Box 2583  
Houston, Texas 77252-2583  
(800) 615-8999  
<http://www.equistarchem.com>



# EQUISTAR