



POLYBATCH® COLOR Yellow 2600V

POLYBATCH® 2600V is a yellow color concentrate based in polyethylene. This concentrate was designed to provide color in polyolefin film and molding applications. POLYBATCH® 2600V contains heavy metal pigment(s) and is typically recommended for use at 5% addition levels.

Properties	Standard	Parameters	Unit
Appearance			
Pellet Count		55	pellets/gram
Chemical			
Moisture (Water Content)		2200 max	ppm
Total Ash		52	%
General			
Melt Flow Rate	ASTM D1238	190°C/2.16kg 14	g/10 minutes
Specific Gravity		1.62	

Reported values pertain only to natural resins: pigmentation may vary properties. Pellet cut, size, color, and other properties may vary depending on the manufacturing location.

NOTE: While the information herein is believed to be reliable and correct, nothing herein is intended and should not be construed as a representation of warranty, expressed or implied as to results obtained or to be obtained by others who may make use of this information or with respect to the absence, existence or validity of patent rights, if any of others involving any composition or process herein referred to; or an inducement or recommendation for the violation of any such patent rights; and responsibility therefore is disclaimed.

POLYBATCH® COLOR Yellow 2600V

- Regulatory Info:** POLYBATCH® 2600V contains materials(s) which do not comply with FDA regulations for food contact applications.
- Storage:** Although no known shelf life has been determined for this concentrate, A. Schulman recommends that inventories are rotated and used within 12 months of purchase for optimum performance.
- Packaging:** POLYBATCH® 2600V is typically packaged in polyethylene lined gaylords or polyethylene bags.
- Safety:** POLYBATCH® 2600V contains material(s) which must be reported in accordance with current OSHA regulations. Please refer to the MSDS for additional safety and regulatory information.

Reported values pertain only to natural resins: pigmenting may vary properties. Pellet cut, size, color, and other properties may vary depending on the manufacturing location.

NOTE: While the information herein is believed to be reliable and correct, nothing herein is intended and should not be construed as a representation of warranty, expressed or implied as to results obtained or to be obtained by others who may make use of this information or with respect to the absence, existence or validity of patent rights, if any of others involving any composition or process herein referred to; or an inducement or recommendation for the violation of any such patent rights; and responsibility therefore is disclaimed.