

Clarity. TOTAL Polypropylene 3276 produces thermoformed parts with good side wall stiffness and gloss.

High Purity. TOTAL Polypropylene 3276 features minimum taste and odor and optimum thermal stability for superior color and processability.

FDA. TOTAL Polypropylene 3276 complies with all applicable FDA regulations and may be used under these provisions for food contact and packaging.

Recommended Applications. TOTAL Polypropylene 3276 is ideal for deli containers, drinking cups, lids, and food service trays.

Processing. TOTAL Polypropylene 3276 resin processes on in-line, narrow web thermoforming and solid phase pressure forming equipment with typical melt temperature at 450°-500°F (232-260°C). Call the nearest TOTAL Polypropylene Sales Office for additional information.

<u>Resin Properties</u> ⁽¹⁾	<u>Typical Value</u>	<u>ASTM Method</u>
Melt Flow, g/10 min.	1.8	D-1238 Condition "L"
Density, g/cc	0.905	D-1505
Melting Point, °F (°C)	330 (165)	DSC ⁽²⁾
<u>Mechanical Properties</u> ⁽¹⁾		
Tensile, psi (M Pa)	5,200 (35.9)	D-638
Elongation, %	10.0	D-638
Tensile Modulus, psi (M Pa)	200,000 (1,380)	D-638
Flexural Modulus, psi (M Pa)	175,000 (1,206)	D-790
Izod Impact @ 73°F		D-256A
Notched-ft.lb./in. (J/m)	0.8 (40.0)	
<u>Thermal Properties</u> ⁽¹⁾		
Heat Deflection		D-648
°F at 66 psi	224	
°C at 4.64 kg/cm ²	107	
<u>Barrier Properties</u> ⁽¹⁾		
Moisture Vapor Transmission @ 100°F(38°), 90% R.H. gms/mil/100 in. ² /24 hrs.	0.45	E-96
Oxygen Transmission, @ 73°F (23°C) cc/100 in ² mil/24 hrs./ atm.	240	D-1434

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.
 (2) MP determined with a DSC-2 Differential Scanning Calorimeter. Test procedure available upon request.

3276 10/04

Corporate Office USA
 P.O. Box 674411
 Houston, TX 77267-4411
 800.344.3462
 877.428.6346
www.totalpetrochemicalsusa.com

Technical Center
 P.O. Box 1200
 Deer Park, TX 77536
 281.884.0500

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of TOTAL products must be guided by the users own methods for selection of proper formulation. TOTAL PETROCHEMICALS USA, INC. disclaims any responsibility for misuse or misapplication of its products. TOTAL MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TOTAL'S liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.