

Low Water Carryover. TOTAL Polypropylene 3365 exhibits excellent low water carryover, which allows extrusion at maximum line speeds.

High Purity. Low catalyst residues in TOTAL Polypropylene 3365 allow extended processing runs without screen pack pluggage.

FDA. TOTAL Polypropylene 3365 complies with all applicable FDA regulations for food contact applications.

Recommended Applications. TOTAL Polypropylene 3365 is recommended for water quench slit films and monofilaments for carpet backing, rope, and cordage products.

Processing. TOTAL Polypropylene 3365 processes on conventional extrusion equipment with typical melt temperatures of 400-500°F (204-260°C). Call the nearest ATOFINA sales office for additional information.

<u>Resin Properties</u> ⁽¹⁾	<u>Typical Value</u>	<u>ASTM Method</u>
Melt Flow, g/10 min.	3.8	D-1238 Condition "L"
Density, g/cc	0.905	D-1505
Melting Point, °F (°C)	330 (165)	DSC ⁽²⁾

Mechanical Properties⁽¹⁾

Tensile Modulus, psi (M Pa)	220,000 (1,515)	D-638
Flexural Modulus, psi (M Pa)	200,000 (1,380)	D-790
Flexural Stiffness, psi (M Pa)	160,000 (1,104)	D-790

Fiber Properties⁽¹⁾⁽³⁾

Tenacity, g/denier	5.8
Elongation, %	28

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

(2) MP determined with a DSC-2 Differential Scanning Calorimeter. Test procedure available upon request.

(3) Samples processed at 6:1 ratio and 450 degrees F (232 degrees C) melt temperature.

3365 10/04

Corporate Office USA
P.O. Box 674411
Houston, TX 77267-4411
800.344.3462
877.428.6346
www.totalpetrochemicalsusa.com

Technical Center
P.O. Box 1200
Deer Park, TX 77536
281.884.0500

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of TOTAL products must be guided by the users own methods for selection of proper formulation. TOTAL PETROCHEMICALS USA, INC. disclaims any responsibility for misuse or miss application of its products. TOTAL MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TOTAL'S liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.