



Formosa Plastics®

Formolene® PP

Formolene 7320B

Random Copolymer for Storage Boxes, Pill Vials and Containers

Formolene 7320B is a high flow random copolymer with fast cycle time and easy mold release. It is designed for injection molding applications. Its clarity makes it an excellent choice for “see-through” housewares and rigid packaging.

Formolene 7320B meets all requirements of the U. S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact.

Typical Properties of this Commercial Grade

Melt Flow Rate, I ₂ @ 230°C, g/10 min	ASTM D1238	20.0
Density, g/cm ³	ASTM D1505	0.9
Tensile Strength at Yield (50 mm/min), psi	ASTM D638	4,400
Elongation at Yield (50 mm/min), %	ASTM D638	12
Flexural Modulus (1.3 mm/min), 1% Secant, psi	ASTM D790	165,000
Rockwell Hardness, R Scale	ASTM D785	100
Notched Izod Impact Strength @ 73°F, ft-lb/in	ASTM D256	0.8
Notched Izod Impact Strength @ 0°C, ft-lb/in	ASTM D256	0.4
Heat Deflection Temperature @ 66psi, °C	ASTM D648	90

Note: Specimens were injection molded according to the conditions specified in ASTM D4101.
Published 5/07, Reviewed 07//07

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (888) FPCUSA3 • Fax: (973) 716-7230

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA PLASTICS CORPORATION, U.S.A. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA PLASTICS CORPORATION, U.S.A. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of FORMOSA PLASTICS CORPORATION, U.S.A. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.



ISO 9001:2000
FS 70459
FM 31429
FM 46020



ISO 14001
EMS 35710