



TR3350C

Random Copolymer Polypropylene

- High Melt Flow, Excellent See-Through Clarity, Superior Color and Processing Stability, Low Odor
- Suggested Uses Include Reusable Food Containers, Housewares, Fast-Cycle Injection Molding

| Property | Units | Typical Value | Test Method |
|--|------------------|------------------|-------------|
| Nominal Melt Flow Rate (230°C/2.16kg) | g/10 min | 35 | ASTM D1238 |
| Tensile Strength at Yield (2 in/min, 50 mm/min) | psi MPa | 4,500 31 | ASTM D638 |
| Elongation at Yield (2 in/min, 50 mm/min) | % | 9 | ASTM D638 |
| Flexural Modulus (0.05 in/min, 1.3 mm/min, 1% secant) | psi MPa | 170,000 1,172 | ASTM D790A |
| Notched Izod Impact Strength at 23°C | ft-lbs/in J/m | 0.9 48 | ASTM D256A |

Information contained herein is considered accurate to our best knowledge. It is offered for your consideration and investigation, and is not to be construed as a representation or warranty, expressed or implied, for which Sunoco Chemicals assumes legal responsibility. Our warranties are limited to those expressly stated in formal contracts or in conditions of sale on our invoices and order acceptances. Conditions and methods of use vary and are beyond the control of Sunoco Chemicals. Sunoco Chemicals, therefore, disclaims any liability incurred as a result of the use of its products in accordance with the data contained herein. No information herein shall be construed as an offer of indemnity for infringement or as a recommendation to use these products in such a manner as to infringe any patent, domestic or foreign.

For cautions and other information relating to handling of and exposure to this product, please see material safety data sheet code number C4027 published by Sunoco Chemicals.

550 Technology Drive
Pittsburgh, PA 15219
1-800-223-8871

Revision Date: 8/24/2005

www.sunocochem.com